Product data sheet	
Product range	Bennett & Jones 14 mm

Product data				
	plank			
Dimensions in mm (L * W * T)	1900 x 190 x 14			
Wear surface	approx. 3,0 mm			
Units / package	8 pieces			
Package	2,889 m² ; 22,5 kg			
Warranty	15 years for private use according to our terms of warranty			
Connection	Click 2G			
Notes	Subject to technical changes, Cleaning and care see instructions please			

Product constructions				
Wear surface	Hardwood			
Middle layer	softwood staves			
Stabilizing layer	poplar			

Product properties					
	Test norm				
Thermal resistance	DIN EN 4108-4	0,13W/mK			
Biological durabilty		class 1			
PCP content		≤5 ppm			
Formaldehyde emission	EN 717 - 2	E1			
Reaction to fire	EN 13501-1	Dfl-s1			
Resistance to chair castors	DIN EN 13329	No impact if soft chair castors are used			
Sorting requirements	EN 13489	Requirements are met by factory sorting			
Laying system	EN 13489	floating, overall glued			
Floor heating		Only suitable for hot water underfloor heating with a maximum surface temperature of 29°C			
Renovation		At least resandable twice with normal wear			
Disposal		Private disposal in the garbage possible			

Tolerances according to EN 13489

Total ances according to 114 Total				
allowed differences in width	± 0,2 mm			
allowed differences in squareness	≤ 0,2 %			
longitudinal curvature	≤ 0,1 %			
Transverse curvature	≤ 0,2 %			
Differences in height	≤ 0,2 mm			
Humidity level on delivery	5-9%			

Other packaging properties	Each pack can contain one board in two pieces (plank format)
Tottler packaging properties	Lacii pack can contain one board in two pieces (plank format)

Surface properties				
	Test norm	laquered	natural oil treated	natural oil treated, brushed
slip resistance	EN 15676	USRV 70	USRV 57	USRV 94
Resistance to staining	DIN 68861 - 1	1B	1C	1C
Scratch resistance	Hamberger Hobe	≥ 20 N	n.n	n.n

Due to its lively appearance, the grading is quite separate from conventional grading criteria. Knots and splits are desirable visual characteristics of the grading, which when subjected to climate fluctuation can lead to the formation of cross going cracks